

LEXANTM HPXXX FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN ™ HPxxX graphic film is a first-surface printable high-performance coated film offering high quality chemical/abrasion resistance, plus very good UV resistance. These performance capabilities, along with LEXAN film's ease of processing, make HPxxX film a good choice for outdoor and indoor graphic applications where color stability and the ability to use light or white ink systems are important. Suitable applications include: Appliance Labels, Warning Labels on Outdoor Equipment, Gasoline Pumps, Outdoor Lenses, Marine Graphics, Outdoor Menu Boards, Any Overlay Where Light or White Inks are used.

TYPICAL PROPERTY VALUES ◆

PROPERTY	ASTM TEST METHOD	UNITS USCS	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	8800	ISO 527	MPa	60
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	62
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.51	ISO 34	kN/m	264
Propagation	ASTM D1922	g/mil	40		kN/m	14
THERMAL						
Vicat Softening Temperature, B	ASTM 1525	°F	320	ISO 320	[©] C	160
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75 Modified	ōС	145
Shrinkage at 302°F (150°C)	ASTM D1204	%	1.40%			1.40%
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.3	ISO 1183	Kg/m³	1200
Surface Energy (1st surface / 2 nd surface)	ASTM D5946-01	-	37/34			
Surface Tension (1st surface / 2 nd surface)	Dyne Pens	Dyne	36-38/38-40			
Pencil Hardness (1st surface / 2 nd surface)	ASTM D3363	-	HB-F/B-HB			
Taber Abrasion	ASTM D1044	delta Haze	11			
OPTICAL						
Light Transmission	ASTM D1003	%	92			
Yellowness Index	ASTM D1925	%	0.7			
Haze	ASTM D1003	%	0.5			
Gloss over Flat Black min/max @ 60	ASTM D523-60	%	92	ISO 2813	%	92
UV %Transmission at 380 nm	UV/Visual Spectroscopy	%	39			

These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.

Reported Values are based on 0.010" (0.250 mm) Thickness unless otherwise noted.

™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.007" (0.175mm)	-10% / +24%
0.010" (0.250mm)	-10% / +20%
0.015" (0.375mm)	-5% / +12%
0.020" (0.500mm)	-5% / +10%

UV RESISTANCE

LEXAN HPxxX film utilizes a proprietary coating technology developed by SABIC. This special coating resists virtually all yellowing and hazing – no matter how bright the sun. With a yellowness index of 3.0 at 1000 hours of QUV testing, LEXAN HPxxX film is a natural choice for demanding outdoor applications and indoor applications where color stability and first-surface printability is important.

CHEMICAL AND ABRASION RESISTANCE

A unique feature of LEXAN HPxxX film is its receptivity to multiple-pass, first-surface decoration for selective textures and/or color graphics. This feature requires that the coating be chemically sensitive to a variety of ink formulations. As a result, the coating is subject to attack by aggressive industrial chemicals and some strong household cleaners. Both the chemical resistance and hardness of the coating can be enhanced by exposing the coated surface of the film to UV ink curing conditions. We recommend that only UV-curable inks which are compatible with LEXAN HP films be used. Please consult the LEXAN HP Films Technical Guide for more details. Along with very good UV resistance, LEXAN HPxxX film also has chemical and abrasion resistance comparable with the original HPS series of films.

TABER ABRASION RESISTANCE (ASTM D1044) LEXAN HPXXX GRAPHIC FILM

CONDITION CS10F WHEEL, 500 GRAMS	UNITS	AS MANUFACTURED	POST CURED ¥
25	Change in % Haze	1.5	2
50	Change in % Haze	2.5	3.4
100	Change in % Haze	3.5	5.5
200	Change in % Haze	7.5	13.1

^{*} Post cure conditions: One elliptical focused medium pressure mercury vapor lamp at 300 watts/inch and a conveyor speed of 20 feet/minute

CHEMICAL RESISTANCE

CHEMICAL	RESULTS ¹	
One Hour Continuous Surface	As Manufactured	Post Cured
Contact at 73° F		
Acetone	Failed	Failed
MEK	Failed	Passed
Toluene	Passed	Passed
Methylene Chloride	Failed	Failed
Isopropyl Alcohol	Passed	Passed
Cyclohexanone	Passed	Passed
Ethyl Acetate	Passed	Passed
40% NaOH	Passed	Passed
Concentrated HCI	Passed	Passed
Gasoline (Regular)	Passed	Passed
Gasoline (Unleaded)	Passed	Passed
Butyl Cellosolve	Failed	Passed

24 hour continuous Surface		* A few small
Contact at 120°F		coating blisters
Coffee	Passed	Passed
Top Job*	Passed	Passed
Fantastik*	Passed	Passed
Formula 409*	Passed	Passed
Windex w/ Ammonia D*	Passed	Passed
Wisk *	Passed	Passed
Downy*	Passed	Passed
Spray N Wash*	Passed	Passed
Clorox*	Passed	Passed
Mustard	Failed	Passed
Mr. Clean*	Passed	Passed
Ketchup	Passed	Passed
Tea	Passed	Passed
Tomato Juice	Passed	Passed
Lemon Juice	Passed	Passed
Grape Juice	Passed	Passed
Vinegar	Passed	Passed
Milk	Passed	Passed

Failure constitutes any of the following: non-removable stain or cloudiness, blistering, delamination, or cracking of the coating or failure to pass crosshatch tape adhesion Wisk is a registered trademark of Lever Brothers Company Formula 409 and Clorox are registered trademarks of the Clorox Company Top Job, Downy, and Mr. Clean are registered trademarks of Procter & Gamble Fantastik and Spray 'N Wash are registered trademarks of Texize, Division of Norton Norwich Products, Inc. Windex w/Ammonia D is a registered trademark of Drackett Products Company

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (o) 1 225 8000
F +966 (o) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe Specialty Film & Sheet

Plasticsíaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293678 F +31 (0)164 293272 E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet 2550 Xiupu Road Pudong 201319 Shanghai China T +86 21 2037 8188 F +86 21 2037 8288 E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCOPPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S TANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates. © 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

 † Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

