



LEXAN™ 6070T FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 6070T Film is a co-extruded film with improved scratch resistance with higher pencil hardness surface. The film has excellent clarity, high heat resistance and excellent formability. LEXAN 6070T Film also provide good dimensional stability and improved pencil hardness. Masking are available on both sides.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	6786	ISO 527	MPa	46.8
Ultimate	ASTM D882	psi	5872	ISO 527	MPa	40.5
Tensile Modulus	ASTM D882	psi	252445	ISO 527	MPa	1741
Tensile Elongation at Break (TD/MD)	ASTM D882	%	22.5	ISO 527	%	22.5

THERMAL

Coefficient of Thermal Expansion						
CTE -20~60°C, crossflow	ASTM E831	(x10 ⁻⁵ /°F)		ISO 11359-2	(x10 ⁻⁵ /°C)	6.2
CTE -20~60°C, inflow	ASTM D831	(x10 ⁻⁵ /°F)		ISO 11359-2	(x10 ⁻⁵ /°C)	6.8

PHYSICAL

Density	ASTM D792	slug/ft ³	2.33	ISO 1183	g/m ³	1.19
Water Absorption, 24 hrs.	ASTM D570	% change	0.41	ISO 62	% change	0.11
Pencil hardness (500g)	ASTM D3363	-	2H		-	2H
Taber Abrasion (100 Cycles)	ASTM D1044	Delta Haze%	16.8		Delta Haze%	16.8
Surface Tension (PMMA surface/ PC surface)	Dyne Pens	Dyne	38/40		Dyne	38/40

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
OPTICAL						
First surface			1.49			
Second surface			1.58			
Light Transmission	ASTM D1003	%	92.1	ISO 489		92.1
Yellowness Index	ASTM E313	%	0.4/0.57			0.4/0.57
Haze	ASTM D1003	%	0.1			0.1
Gloss over Flat Black	ASTM D523-60	-		ISO 2813		
@ 20°			83.2			83.2
@ 60°			88.3			88.3
@ 85° (PMMA surface)			97.7			97.7

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010”) thickness film and are tested at machine direction unless otherwise noted.

™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.007” (0.178mm)	-/+ 10%
0.010”-0.015” (0.178mm-0.381 mm)	-/+ 5%



CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Americas

Functional Forms
2500 City West
Boulevard Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E ff.info@sabic.com

Asia Pacific

Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (“SELLER”) ARE SOLD SUBJECT TO SELLER’S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER’S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER’S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller’s materials, products, services or recommendations for the user’s particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller’s Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2020 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.