

LEXAN™ EFR65 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ EFR65 is one side fine matt and one side velvet of both clear and black color environmental friendly flame-retardant polycarbonate film with a UL94 VTM-0 listing at 0.100 mm (BK) and 0.127 mm (NC). This film has formability, excellent mechanical properties, good dimensional stability at high temperatures and a high flammability rating, making it good for applications such as power supply insulation, disc drive insulation, bus-bar insulation, TV/monitor insulation, PC board insulation, business equipment insulation and has insulation and EMI/RFI shielding when laminated with metal foil.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield	ASTM D882	psi	7832	ISO 527	MPa	54
Ultimate	ASTM D882	psi	8267	ISO 527	MPa	57
Tensile Modulus	ASTM D882	psi	295700	ISO 527	MPa	2039
Tensile Elongation at Break	ASTM D882	%	>90	ISO 527	%	>90
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.23		kN/m	215
Propagation	ASTM D1338	g/mil	30.8		kN/m	11.9
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb/in	416		J/mm	22.2
Fold Endurance (MIT)	ASTM D2176-97a	double folds				
0.010" (0.254 mm) (MD/TD)			74/50			
0.017" (0.432 mm) (MD/TD)			25/21			
0.020" (0.508 mm) (MD/TD)			18/18			
THERMAL						
Coefficient of Thermal Conductivity @25°C	ASTM E1530	Btu-in/(hr-ft ² -°F)	1.66		W/m-K	0.24
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.6	ISO 11359	(x10 ⁻⁵ /°C)	6.4
Specific Heat @ 25°C	ASTM E1269-05	Btu/(lb-°F)	0.29		KJ/Kg-°C	1.23
Glass Transition Temperature	ASTM D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B @ 50N, 120°C/h	ASTM 1525	°F	303		°C	151
Heat Deflection Temp. by TMA at 1.8 Mpa	ASTM D648	°F	267	ISO 75 Modified	°C	131
Shrinkage at 302°F (150°C/0.5h)	ASTM D1204					
MD		%	1.2		%	1.2
TD		%	0.23		%	0.23
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.33	ISO 1183	kg/m ³	1200
Surface Tension	Dyne Pens	Dyne	36			

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
OPTICAL						
Refractive Index @ 25°C (NC color)	ASTM D542-00		1.6			
Light Transmission (NC color)	ASTM D1003	%	92.6			
Yellowness Index (NC color)	ASTM E313	%	<1.0			
Haze (NC color)	ASTM D1003	%	97.2			
Gloss over Flat Black min/max @ 60° (Fine Matte/Velvet)	ASTM D523-60	-	5.0/5.7	ISO 2813	-	5.0/5.7

ELECTRICAL						
Dielectric Strength in oil, short time @ 77°F (25°C)	ASTM D 149-97a Method A			IEC 60243		
10 mils (0.254mm)		kV/mil	1.73		kV/mm	68.1
Dielectric Constant @ 60 Hz	ASTM D150	-	2.29	IEC 60250	-	2.29
@1,000,000 Hz		-	2.94		-	2.94
Dissipation Factor @ 60 Hz	ASTM D150	-	0.001	IEC 60250	-	0.001
@1,000,000 Hz		-	0.006		-	0.006
Volume Resistivity	ASTM D257	Ω-cm	>1.0E+17	IEC 60093	Ω-cm	>1.0E+17
Surface Resistivity	ASTM D257	Ω/square	>1.0E+16	IEC 60093	Ω/square	>1.0E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	123			

- ◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported Values are based on 0.250 mm (0.010") thickness unless otherwise noted.
- ™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.004 - 0.007" (0.100 - 0.178mm)	± 10%
0.010 - 0.022" (0.254 - 0.550mm)	± 5%

Black Color – 701 (BK)
 Natural Color – NC

UL File Number: [E121562](#), [E207780](#)

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 293272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2020 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.