

# LEXANTM SD8A12 FILM

## PRODUCT DATASHEET

#### **DESCRIPTION**

LEXAN<sup>TM</sup> SD8A12 Film is a one side polished, high gloss (P), one side fine matt (FM) clear transparent polycarbonate film that is typically used in government security documents, such as passport data pages, ID cards, driving licenses, It offers great printability and ease of processing (laminating, die-cutting, hot stamping). LEXAN<sup>TM</sup> SD8A12 Film is available in gauges ranging from 50 - 100 $\mu$ m.

## TYPICAL PROPERTY VALUES◆

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL				T		
Tensile Strength @ Yield	ASTM D882	psi	8122	ISO 527	MPa	56
Ultimate	ASTM D882	psi	8122	ISO 527	MPa	56
Tensile Modulus	ASTM D882	psi	311 x10 <sup>3</sup>	ISO 527	MPa	2150
Tensile Elongation at Break	ASTM D882	%	85	ISO 527	%	85
Tear Strength						
Initiation	ASTM D1004	lbf	12	ASTM D1004	N	52
Propagation	ASTM D1938	lbf	0.6	ASTM D1938	Ν	2.8
THERMAL						
Coefficient of Thermal Expansion, flow	ASTM E831	(x 10 <sup>-5</sup> / °F)	4.2	ISO 11359	(x 10 <sup>-5</sup> / °C)	7.5
Glass Transition Temperature	ASTM D3418	°F	298	ISO 11357	°C	148
Vicat Softening Temperature, B50	ASTM 1525	°F	295	ISO 306	°C	146
Heat Deflection Temp. Af 120°C/h	ASTM D648	°F	262	ISO 75 Modified	°C	128
Shrinkage at 130°C, 30min	Internal method	%	0.17	Internal method	%	0.17
PHYSICAL						
Density	ASTM D792	slug/ft3	2.33	ISO 1183	g/cm3	1.20
Water Absorption, 24 hrs.	ASTM D570	% change	0.09	ISO 62	% change	0.09
Surface Roughness Ra		μin	23[FM]	ISO4288	μm	0.6 [FM]
			7[P]			0.18[P]
Surface Tension	Dyne solutions	Dyne/cm	38 [FM]	Dyne solutions	Dyne/cm	38 [FM]
			40 [P]			40 [P]
OPTICAL						
Light Transmission	ASTM D1003	%	90	ASTM D1003	%	90
Color: b-value	CIELab, Reflection,		-0.87	CIELab, Reflection,		-0.87
	D65, 10°			D65, 10°		

These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are based on 0.050 mm (0.002") thickness film, except for the Coefficient of thermal expansion, Vicat softening temperature, Heat deflection temperature and water absorption, which are based on molded parts.

<sup>™</sup> Trademark of SABIC.

#### MANUFACTURING SPECIFICATIONS

**NOMINAL GAUGE RANGES** 0.050 - 0.100 mm

MIN./MAX LIMIT OF NOMINAL

± 5%

### **CONTACT US:** SABIC CORPORATE HQ

PO Box 5101 Riyadh 11422 Saudi Arabia

T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com

**AMERICAS** 

SABIC Functional Forms 2500 CityWest Boulevard Suite 100 Houston, TX 77042

USA

Toll-free (800) 323 3783 F (888) 443 2033

E spinside.sales@sabic.com

**EUROPE** 

SABIC Functional Forms Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293684

F +31 (0)164 292272

E ff.info@sabic.com

T +86 21 3222 4500 F +86 21 6289 8998 Eff.info@sabic.com

**PACIFIC** 

Pudong

China

**Functional Forms** 

2550 Xiupu Road

201319 Shanghai

SABIC

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. intellectual property right.

SABIC and brands marked with  $^{\mbox{\scriptsize TM}}$  are trademarks of SABIC or affiliates. © Copyright 2021 All rights reserved.

 $^\dagger Any$  brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

