

LEXAN™ SD8A92 FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN[™] SD8A92 Film is a one side polished, high gloss (P), one side fine matte (FM) clear transparent laser markable polycarbonate film that is typically used in government security documents, such as passport data pages, ID cards, driving licenses, ... It offers great printability and ease of processing (laminating, die-cutting, hot stamping). LEXAN[™] SD8A92 Film is available in 50 and 100µm.

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALU
MECHANICAL		(,				
Tensile Strength @Yield	ASTM D882	psi	7830	ISO 527	MPa	54
@Break	ASTM D882	psi	9700	ISO 527	MPa	67
Tensile Modulus	ASTM D882	psi	300 x10 ³	ISO 527	MPa	2080
Tensile Elongation at Break	ASTM D882	%	137	ISO 527	%	137
Tear Strength						
Initiation	ASTM D1004	lbf	12	ASTM D1004	Ν	52
Propagation	ASTM D1938	lbf	0.6	ASTM D1938	Ν	2.8
THERMAN						
THERMAL Coefficient of Thermal	ASTM E831	(x 10 ⁻⁵ / °F)	4.2	ISO 11359	(x 10 ⁻⁵ / °C)	7.5
Expansion, flow	ASTINLOST		4.2	130 11337	(x 10 7 C)	7.5
Glass Transition	ASTM D3418	°F	298	ISO 11357	°C	148
Temperature						
Vicat Softening	ASTM 1525	°F	295	ISO 306	°C	147
Temperature, B50 Heat Deflection Temp. Af	ASTM D648	°F	262	ISO 75 Modified	°C	127
120°C/h	A3110 D040	I	202	13075 Modified	C	127
Shrinkage at 130°C, 30min	Internal method	%	0.17	Internal method	%	0.17
DUNCION						
PHYSICAL Density	ASTM D792	slug/ft3	2.33	ISO 1183	g/cm3	1.20
Water Absorption, 24 hrs.	ASTM D570	% change	0.09	ISO 62	% change	0.09
Surface Roughness Ra		μin	23[FM]	ISO4288	μm	0.6 [FM]
			7[P]			0.18[P]
Surface Tension	Dyne solutions	Dyne/cm	44 [FM]	Dyne solutions	Dyne/cm	44 [FM]
			38 [P]			38 [P]
OPTICAL						
Light Transmission	ASTM D1003	%	88	ASTM D1003	%	88
Color: b-value	CIELab, Reflection,		-1.0	CIELab, Reflection,		-1.0
	D65, 10°			D65, 10°		

These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Specialty Film & Sheet representative or the Quality Services Department. Reported Values are based on 0.100 mm (0.004") thickness film, except for the Coefficient of thermal expansion, Vicat softening temperature, Heat deflection temperature and water absorption, which are based on molded parts.

™ Trademark of SABIC.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.050 - 0.100 mm	± 5%

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com

AMERICAS

SABIC Functional Forms 2500 CityWest Boulevard Suite 100 Houston, TX 77042 USA Toll-free (800) 323 3783 F (888) 443 2033 E spinside.sales@sabic.com

EUROPE

SABIC Functional Forms Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293684 F +31 (0)164 292272 E ff.info@sabic.com

PACIFIC

SABIC Functional Forms 2550 Xiupu Road Pudong 201319 Shanghai China T +86 21 3222 4500 F +86 21 6289 8998 E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates. © Copyright 2021 All rights reserved.

[†]Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

