

COMPEX™ R600
Release Film

Ideally suited to debulking applications.

FEATURES & BENEFITS

- High temperature, tough fluoropolymer release film with excellent release characteristics combined with high elongation.
- Suitable for use with all commonly used resin systems.
- Clear blue for ease of identification on the cured laminate.

PROPERTIES

Maximum use temperature	232°C / 450°F
Color	Clear blue
Film	Fluoropolymer
Standard perforation patterns	P1, P3, P6 and P8
Tensile strength (at break)	42-1 to 70MPa / 6106 to 10152psi
Elongation (at break)	350%
Density	1.75g/cm ³ / 1.01oz/in ³

AVAILABILITY

Thicknesses	12, 15 and 20µm	0.0005, 0.0006 and 0.0008in
Standard width	1.30 and 1.55m	1.42 and 1.69yd
Standard length	150m	164yd
Internal core size	76mm	3in

STORAGE

Store in original packaging.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

CONTACT US:

Shadowline Polimer / Atatürk Mahallesi Erzincan Sokak No:19 34758 Ataşehir, İstanbul/Türkiye
T: + 90 216 575 1162 | F: + 90 216 577 2549 | info@shadowline.com.tr