COMPEX™ R620 Release Film



Ideally suited to aerospace applications.

FEATURES & BENEFITS

• High temperature, tough fluropolymer release film with excellent release characteristics combined with high elongation.

• Suitable for use with all commonly used resin systems.

Most commonly used in aerospace applications and has numerous OEM approvals.

Clear blue or red for ease of identification on the cured laminate.

· Available perforated or non-perforated.

PROPERTIES

Maximum use temperature	232°C / 450°F	
Color	Blue and red	
Film	ETFE	
Standard perforation patterns	Contact us for full details	
Tensile strength (at break)	41.37MPa / 6000psi	
Elongation (at break)	350%	
Yield	10.2m²/kg / 110 ft²/lb/mil	

AVAILABILITY

Thicknesses	12, 15, 20 and 25µm	0.0005, 0.0006, 0.001 and 0.002in
Standard length	Available on request	

STORAGE

Store in original packaging.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

