

FEATURES & BENEFITS

- Tough, high elongation elastomeric film, suitable for de-bulking applications and oven curing of composites up to temperatures of 150°C (302°F).
- Due to the film's high elasticity, the necessity for pleats is reduced in debulk operations.
- Premium film for wind energy applications.
- Good release from sealant tape.

PROPERTIES

Maximum use temperature	150°C (302°F)		
Color	Yellow		
Tensile strength at break (ASTM D882)	Transverse Direction Machine Direction	40 MPa 37 MPa	5802PSI 5366PSI
Elongation at break (ASTM D882)	Transverse Direction Machine Direction	370% 360%	
Yield	50µm (0.002in) 65µm (0.0025in) 75µm (0.003in)	19.12m ² /kg 14.71m ² /kg 12.74m ² /kg	10.37yd ² /lb 7.98yd ² /lb 6.91yd ² /lb

AVAILABILITY

Thickness	50,65 and 75µm	0.002, 0.0025 and 0.003in
Roll Weight	Up to 45kg	Up to 100lbs
Widths	Up to 10.05m (open)	Up to 394in (open)
Formats available	Tube, sheet, V sheet, gusseted and C-fold	

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

STORAGE

VF-150AW is a hydrophilic material. Moisture and water act as plasticizers. The level of moisture content at time of use is therefore an important factor for successful performance. The higher the moisture content the more flexible they become. Conversely at lower moisture levels flexibility is limited. Do not store rolls vertically on their ends.

CONTACT US:

Shadowline Polimer / Atatürk Mahallesi Erzincan Sokak No:19 34758 Ataşehir, İstanbul/Türkiye
T: + 90 216 575 1162 | F: + 90 216 577 2549 | info@shadowline.com.tr

