

## FEATURES & BENEFITS

- Multi-layer vacuum bagging film produced using our state of the art co-extrusion technology.
- Suitable for high temperature autoclave curing of aerospace composites, including BMLs.
- Soft and supple with unprecedented tensile strength for added security.
- Unique formulation less sensitive to low humidity conditions than standard nylon films.

## PROPERTIES

Maximum use temperature	204°C	400°F
Color	Pink	
Tensile strength at break (ASTM D882)	96.53 MPa	14000PSI
Elongation at break (ASTM D882)	475%	
Yield	17.4m <sup>2</sup> /kg (50µm) 11.6m <sup>2</sup> /kg (75µm)	9.44yd <sup>2</sup> /lb 6.29yd <sup>2</sup> /lb

## AVAILABILITY

Thickness	50 and 75µm	0.002 and 0.003in
Roll Weight	Up to 45kg	Up to 100lbs
Widths	4.06m (open)	160in (open)
Formats available	Tube, sheet, V sheet, gusseted and C-fold	

## HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

## STORAGE

Do not store rolls vertically on their ends.

### CONTACT US:

Shadowline Polimer / Atatürk Mahallesi Erzincan Sokak No:19 34758 Ataşehir, İstanbul/Türkiye  
T: + 90 216 575 1162 | F: + 90 216 577 2549 | info@shadowline.com.tr

