

PRODUCT DATASHEET

LEXAN™ F6000 Sheet

DESCRIPTION

LEXAN™ F6000 sheet is a flame retardant opaque polycarbonate sheet range available in standard and custom colors. In addition to good flammability performance, it offers excellent impact resistance, good stiffness and strength and ease of processing, making it suitable for a wide variety of applications in industries such as electrical/electronics and transportation (e.g. aircraft, rail).

TYPICAL PROPERTY VALUES ♦

Property	Test Method	Units	Value
Physical			
Density	ISO 1183	g/cm ³	1.21
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
Mechanical			
Yield stress 50 mm/min	ISO 527	Mpa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
Impact			
Charpy impact, notched, 3.0 mm	ISO 179/1C	kJ/m ²	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	70
Thermal			
Vicat softening temperature, B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
Electrical			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
Optical			
Light transmission (Y) 3 mm	ASTM-D1003	%	n/a
Fire Ratings			
Aircraft			
Vertical burn, 60 s	FAR 25.583(a)+App.F	-	Pass (1-6mm)
Smoke density	ABD0031	-	Pass, Ds(4min)<150 (1-6mm)
Smoke toxicity	ABD0031,BSS 7239	-	Pass (1-6mm)
Rail			
France	NF P 92-501	-	M2 (2mm)
France	NF F 16-101	-	F2 (2mm)
UK	BS 6853	-	Ao=0.125
Germany	DIN 5510-2	-	S4/ST2/SR2, FED<1 (1mm) S4/ST2/SR1, FED<1 (1.5-4mm)
Electrical			
Vertical burn (50W)	UL94	-	V0 (1.5-6mm)
Limited Oxygen Index	ISO 4589-2	%	35

♦ Typical values only. Variations within normal tolerances are possible for the various textures.

™ Trademarks of SABIC.

PRODUCT DATASHEET

LEXAN™ F6000 Sheet

PROCESSING

Lexan F6000 sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. Lexan F6000 sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least 3° should be allowed, and post mold shrinkage of 0.3 – 0.8% taken into account, depending on mold temperature.

PRE-DRYING

It is important to ensure that Lexan F6000 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying of 2 hours/mm thickness

ASSEMBLING

Parts made from Lexan F6000 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC Innovative Plastics, Film & Sheet representative for advice on specific applications.

PAINTING

Lexan F6000 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available upon request.

CHEMICAL RESISTANCE

Lexan F6000 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the Lexan F6000 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance.

PRODUCT AVAILABILITY

Product code: Lexan F6000

Textures: Polished/Suede (F6006), Polished/Haircell (F60011N)

See product availability guide for available gauges, sizes, and colors

Americas Headquarters

SABIC Innovative Plastics
One Plastics Avenue
Pittsfield, MA 01201
USA
T +1-413-448-7125
Toll-free: 1-800-323-3783
F +1 (888) 443-2033
sfsustomerservice@sabic-ip.com

European Headquarters

SABIC Innovative Plastics
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 293272
Sfs.info@sabic-ip.com

Pacific Headquarters

SABIC Innovative Plastics
Specialty Film & Sheet
1266 Nanjing Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 62881088 ext. 6733
F +86 21 6288 0818

E-mail

sfsustomerservice@sabic-ip.com



* Trademark of SABIC Innovative Plastics IP BV

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right. SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

™ Trademark of SABIC.

sabic-ip.com/sfs